

## TECHNICAL DATA SHEET

### MMA GP Silicone Sealant

#### PRODUCT DESCRIPTION

MMA GP Acetoxy Silicone is a versatile, single-component construction sealant that undergoes acetic cure, reacting with atmospheric moisture to form a resilient rubber seal. Designed for multipurpose applications, it delivers high strength, durability, and elasticity upon curing.

#### TECHNICAL PROPERTIS



Properties	Test Method	Unit	Specifications
Chemical Base			1-C Silicone
Cure Mechanism			Moisture
Cure Type			Acetoxy
<b>As Supplied @ 25°C, 50% RH</b>			
Color			Clear, White, Black
Consistency			Homogeneous paste
Density	ASTM D 1475		0.95 ± 0.02
Flow Properties	ASTM C 639	mm	0 (Non-sag)
Skin Over Time	ASTM C 679	minutes	Approx. 5 - 10
Tack Free Time	ASTM C 679	minutes	Approx. 20 - 30
Depth Cure, 24 hrs	Lab Test	mm	2-4
<b>As Cured – 7 Days @ 25°C, 50% RH</b>			
Hardness (Shore A)	ASTM D 2240	Points	15 – 20
Tensile Strength	ASTM D 412	N/mm <sup>2</sup>	< 1.20
Elongation	ASTM D 412	%	≤ 750
Tensile @100% elongation, N/mm <sup>2</sup> , approx.	ASTM D 412	MPa	0.25 – 0.30
Service Temp.		°C	-20 to +220
Application Temp.		°C	5 to 45

Note:

\* Curing time (Skin Over Time & Tack Free Time) may vary depending on climatic condition during application.

\* Information on this data sheet is subject to change without prior notice and should not be used for writing specifications

TYPICAL USES	KEY FEATURES
<ul style="list-style-type: none"> <li>• General Purpose Sealing and bonding</li> <li>• Suitable for indoor and outdoor applications.</li> <li>• Ideal for use in residential, commercial, and industrial settings.</li> <li>• Sealing masonry joints, balcony, window, and door perimeter joints</li> <li>• Galvanized metal joints</li> </ul>	<ul style="list-style-type: none"> <li>• High-Flexibility</li> <li>• Multi-Purpose</li> <li>• Easy to apply and offers excellent adhesion to nonporous substrates like glass, glazed ceramic tiles, and aluminum.</li> <li>• Antibacterial</li> </ul>

<b>COLORS</b>	MMA GP SILICONE SEALANT is available in Clear, White, Black and Grey. RAL* colors are available upon request. *Special color orders may require lead time and minimum order quantities.
<b>PACKAGING</b>	MMA GP SILICONE SEALANT is available in collapsible tube (90ml), standard caulking cartridges (280 ml) and 200 Liter drum.
<b>SURFACE PREPARATION</b>	The substrate areas that will be in contact with sealant must be clean, dry and free of all loose materials, dust, dirt, rust, oil and other contaminants. Non - porous substrates should be cleaned with a solvent and a clean, lint - free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface.
<b>JOINT DIMENSIONS</b>	Joint dimensions: Min. width for joints: 5 mm, Max. width for joints: 30 mm, Min. depth for joints: 5 mm. <b>Recommendation Sealing jobs:</b> Joint width= 2 X Joint depth
<b>JOINT DESIGN</b>	The movement capability of the sealant must be considered to decide the joint design. In order to reduce the deformations of the joints, depth must be less than width. Depths should be preferably half of the width and it's adjusted by the use of a backup material.
<b>TOOLING AND FINISHING</b>	Immediately tool sealant after application and before skin formation. Tooling of sealant should be done in one continuous stroke. Remove masking tape immediately after tooling is completed.
<b>CLEANUP AND REMOVAL</b>	Uncured sealant may be removed from tools, equipment and non-porous surfaces with solvents. For porous substrates, allow the sealant to cure before removal by peeling or other mechanical means. Cured sealant can only be removed mechanically.
<b>LIMITATIONS</b>	Not paintable. May not be suitable to join sensitive natural stones such as marble, granite or quartz, as this may cause staining. Not to be used in contact with sensitive metals such as lead, copper, brass, zinc, carbon steel, galvanized iron or magnesium as corrosion may occur during acetic acid release/sealant cure. Substrate compatibility test is always recommended.
<b>STORAGE AND SHELF LIFE</b>	When stored in original unopened container at or below 77°F (25°C) in dry warehouse conditions, MMA GP SILICONE SEALANT has a shelf life of 12 months from manufacturing date. Containers should always be kept sealed when not in use.
<b>HANDLING PRECAUTIONS</b>	Use in well-ventilated area. Direct contact of uncured sealant irritates eyes and may irritate skin. Over exposure to vapor may irritate eyes, nose and throat. Do not handle contact lenses with sealant on hands. In case of eye contact, flush eyes with water for 15 minutes. Obtain medical attention. In case of skin contact, remove from skin and flush with water.

KEEP OUT OF REACH OF CHILDREN • KEEP CONTAINER TIGHTLY CLOSED • FOR INDUSTRIAL & PROFESSIONAL USE

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. MMA reserves the right to change the properties of its products without notice